



## Morashopprimer

### Product Description

Morashopprimer is a two-component epoxy based primer with a durable polymer structure.

### Intended Uses

It is used to protect the sand blasted steel during production, transportation, and storage processes.

### Physical Properties

Physical State	: Liquid
Colour	: Oxide Red
Volume Solid (%)	: 31 ± 2
Density	: 1.27 ± 0.03 Kg/L
Gloss	: Matt
Flexibility	: Good

### Application Data

Mixing Ratio (by weight)	: 8,5 units Part A / 1,5 units Part B
Application Methods	: Airless spray, conventional spray
Application Conditions	: The temperature of the substrate should be minimum 3°C above the dew point of the air. Good ventilation is required.
Thinner/Cleaner	: Morashopprimer Thinner

### Guiding data for airless spray

Pressure at nozzle	: 5-7 MPa (150 kp/cm <sup>2</sup> 2100 psi)
Nozzle tip	: 0,15-0,23 mm (0,015-0,021")
Spray angle	: 50-95°
Filter	: Check to ensure that filters are clean.

	Dry (µm)	Wet (µm)	Theoretical Coverage (m <sup>2</sup> /L)
Typical film thickness	20	74	13,50
Maximum thickness	25	93	10,80

<b>Moravia</b>	<b>TECHNICAL DATA SHEET</b>	Document No / Rev.	TDS 064 / 02
		Date	11/08/2017
		Page No	2 / 2

### Surface Preparations

All surfaces to be coated should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### **Steel surface**

Blast-cleaning to Sa 2½ (ISO-8501). Please contact Moravia office for further information.

### Drying Time

Substrate Temperature	Pot Life	Over coating Data	
		Minimum	Maximum
20°C	24 hrs	6 hrs	-

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

**Packing Size** : 20 kg

### **Storage**

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated area and away from source of heat and ignition. Containers must be kept tightly closed.

### **Health and Safety**

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

**Disclaimer:** The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.