# Moravia

## **TECHNICAL DATA SHEET**

Document No / Rev. TDS 098 / 00
Date 05.03.2015
Page No 1 / 2



# **Moralight**

## **Product Description**

Moralight is single component synthetic resin based light-reflective luminous topcoat. Fluorescent pigments inside make the surface more visible and light reflective.

#### **Intended Uses**

It is suitable for warning signs and life-saving equipments.

**Physical Properties** 

Physical State : Liquid

Colour : Orange, Yellow

Volume Solid (%) :  $53 \pm 2$ 

**Density** :  $1,15 \pm 0,05 \text{ kg/L}$ 

Gloss : Glossy Flexibility : Good

**Application Data** 

Mixing Ratio (volume) : Single component

**Application Methods**: Airless spray, conventional spray, brush or roller

**Application Conditions**: The temperature of the substrate should be minimum 3°C above the

dew point of the air. Good ventilation is required.

Thinner/Cleaner : Moravia 009 Thinner

**Guiding data for airless spray** 

Pressure at nozzle : 15 MPa (150 kp/cm² 2100 psi)
Nozzle tip : 0.38-0.53 mm (0.015-0.021")

Spray angle :  $40-80^{\circ}$ 

Filter : Check to ensure that filters are clean.

Typical film thickness

Maximum thickness

| Dry (μm) | Wet (µm) | Theoretical Coverage (m²/L) |  |
|----------|----------|-----------------------------|--|
| 40       | 75       | 13,25                       |  |
| 50       | 95       | 10,60                       |  |

## Moravia

#### **TECHNICAL DATA SHEET**

Document No / Rev. TDS 098 / 00
Date 05.03.2015
Page No 2 / 2

#### **Surface Preparations**

All surfaces to be coated should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### Steel surface

Blast-cleaning to Sa  $2\frac{1}{2}$  (ISO-8501). Power tool cleaning to min. St 2 (ISO 8501) may be acceptable, subject to exposure conditions.

#### Coated surface

The existing paint shall be abraded with #360 sandpaper. Please contact Moravia office for further information.

## **Drying Time**

| Substrate   | Touch Dry | Hard Dry | Over coating Data |         |
|-------------|-----------|----------|-------------------|---------|
| Temperature |           |          | Minimum           | Maximum |
|             |           |          |                   |         |
| 10°C        | 8 hrs     | 40 hrs   | 8 hrs             |         |
| 23°C        | 3 hrs     | 24 hrs   | 3 hrs             |         |
| 30°C        | 2 hrs     | 12 hrs   | 2 hrs             |         |
|             |           |          |                   |         |

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Packing Size : 0.75 L, 2.5 L

#### Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated area and away from source of heat and ignition. Containers must be kept tightly closed.

## **Health and Safety**

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

**Disclaimer:** The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Fevzi Cakmak Cad. No: 2 Sefakoy / Kucukcekmece / Istanbul / Turkey Tel: +90 212 5791336 Fax: +90 212 4265512 Web: www.moraviapaint.com